



Product Data

Castrol Optigear Synthetic X

Synthetic gear oils

Description

Castrol Optigear™ Synthetic X is based on synthetic hydrocarbons and a special plastic deformation (PD) and surface improvement additive package.

The additive package, when activated by high specific loads and corresponding temperatures, helps to equalize surface roughness without creating abrasion leading to the surface improvement (plastic deformation.)

Optigear Synthetic X is a CLP-HC gear oil (according to DIN 51502) and exceeds the minimum requirements according to DIN 51517, part 3, CLP gear oils.

Application

Optigear Synthetic X may be used in spur gear, bevel gears or planetary gear units and in heavy loaded gear units, e.g. wind turbine main gears. It is also suitable for the lubrication of oil-lubricated rolling bearings.

Depending on the specific application, Optigear Synthetic X may be used in an operating temperature range from -30 °C to +95 °C.

Advantages

- High load carrying capacity
- Superior micro pitting protection
- Excellent friction reduction
- Good filtration properties
- Excellent bearing lubrication suitability

Typical Characteristics

Test	Method	Units	X 150	X 220	X 320	X 460
ISO Viscosity Grade	ASTM D 2422	-	150	220	320	460
Density at + 15°C	ISO 12185 / ASTM D4052	g/ml	0.847	0.850	0.854	0.856
Kinematic Viscosity @ 40°C @ 100°C	ISO 3104 / ASTM D445	mm ² /s	146	218	325	459
		mm ² /s	19.0	25.9	34.9	45.0
Viscosity Index	ISO 2909 / ASTM 2270		148	151	152	153
Flash Point, COC	ISO 2592 / ASTM D92	°C		> 250		
Pour Point	ISO 3016 / ASTM D97	°C	-39	-33	-33	-27
Rust Test Procedure A (24 hrs Distilled Water)	ISO 7210 / ASTM D665		Pass	Pass	Pass	Pass
Procedure B (24 hrs Synthetic Sea Water)			Pass	Pass	Pass	Pass
Copper Corrosion (3 hrs @ 100°C)	ISO 2160 / ASTM D130		1a	1a	1a	1a
FE8 wear test (81212MPB- 7.5/80-80)	DIN 51819-3	mg		<10		
Roller wear		mg		<10		
Cage wear FZG test						
A/8.3/90 scoring load stage	DIN 51354			>12		
A/16.6/90 scoring load stage				12		
FZG micropitting test	FVA No. 54			>10		
Foam Sequence I	ISO 6247 / ASTM D892	mls		<100/10		
Ageing behavior, Increase of viscosity at 100°C after 1000 h	ASTM D 2893	%		2		

Subject to usual manufacturing tolerances.

Additional Information

Optigear Synthetic X gear oil can be applied by an oil can, oil cup reservoir, splash, spray mist or by automatic dispensing equipment and central or circulation systems.

It is compatible with mineral oils and esters. This means that traces up to 3% of previous oil in the gear case after draining will not pose any problems. However, the beneficial effects of the special PD additives are reduced when mixed with other gear oils.

Castrol Optigear Synthetic X
18/11/2005, Global Version Number 1
Castrol, Optigear and the Castrol logo are trademarks of Castrol Limited, used under licence.

All reasonable care has been taken to ensure that the information contained in this publication is accurate as of the date of printing. However, such information may, nevertheless, be affected by changes in the blend formulation occurring subsequent to the date of printing. Material Safety Data Sheets are available for all Castrol Ltd products. The MSDS must be consulted for appropriate information regarding storage, safe handling and disposal of a product.

Castrol (UK) Ltd, Industrial Lubricants & Services
Wakefield House, Aspect Park, Pipers Way, Swindon, Wiltshire SN3 1RE, UK
Tel.: +44 (0)845 964 51 11, Fax: +44 (0)1793 486 083

www.castrol.com/industrial